

Application Industry: Water-based Ink Latex paint Adhesive

Product Name: Antifoam RK-9110S

RK-9110Sis a defoamer specially designed for various water-based inks and latex systems. It has excellent dynamic defoaming, antifoaming performance, long-lasting defoaming ability, and excellent compatibility. It has the properties of silicon type defoamer and the compatibility of non-silicon type defoamer. It is used in inks, latex paints and coatings, which improves the leveling and wetting of inks, paints and paints, and improves the abrasion resistance and smoothness of paints.

Product property:

Excellent compatibility

Excellent dynamic defoaming and antifoaming ability

Suitable for a variety of resin systems

Item	Range
Appearance	Milky-white liquid
Viscosity(25°C)	2000~5000mPa·s
Solid content	50±1%
pH value	6.5~8.5

Main physical and chemical properties:

Application Process:

Can be added directly in the manufacturing process, or can be used after pre-dispersion of materials.

In the production of paints, it is recommended to add 50% of the total amount before grinding, and then add 50% after grinding to achieve the best results.

For different temperature of system and stirring factors, adding 0.2-0.5% of the total formula can achieve the good result. Small test before using to achieve the best dosage.

Key Applications

Water based ink Production and manufacture of adhesives Production and manufacture of various of latex paint Various of water based paint, that pay more attention to the grinding process

LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses



ll Technology CO., Ltd. th Road, Siming District, Xiamen City,

Product content

Pure or mixture	Mixture
English name	Polyether modified silicone

Dangerous marks

Human-body health effect	Skin	Slightly skin allergic for variety of	
	contact	people	
	Eye contact	Eye allergic	
	Swallow	No data	
Environment effect	No data		
Physical/chemical damage			
Special damage			

Packaging & Storage

Package	25kg/ 50kg/120kg/ 200kg plastic pail or 1000kg IBC
Storage Condition	Room Temperature Storage (5°C-40°C), Avoid direct sun light, shelf
	life is 6 months.

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained here is offered in good faith and is believed to be accurate. However, because conditions and methods of use of Rickman products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end application.